

## Model Formula

### MegaRez<sup>TM</sup> SA-857 Solution Acrylic Resin in Xylene

#### White Concrete stain (SA857-1)

<u>Material</u>	<u>Weight (lbs)</u>	<u>Stage</u>
Xylene	117.00	Pigment grind stage: HSD mixer - mix 20 min.
MegaRez <sup>TM</sup> SA-857	437.40	
Clay suspending agent	13.50	
Pigment Dispersant	9.60	
Alumina silicate	135.50	
Titanium Dioxide	91.25	
Xylene	96.50	Thin-down
Aromatic 100	31.80	
20% C.B dispersion	2.00	
Non-Silicone defoamer	1.90	

**TOTAL:** 936.45 lbs

#### PAINT SPECIFICATIONS:

<b>Density:</b>	<b>9.36 lb/gal</b>	<b>Solids wt%:</b>	<b>48.23 %</b>
<b>PVC:</b>	<b>16.9</b>	<b>VOC:</b>	<b>581 g/L</b>

The information and recommendations set forth in this literature are based upon tests conducted by or on behalf of Omega Specialty Products & Services, LLC. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Omega Specialty Products & Services representative to obtain the most recent literature.

Omega Specialty Products & Services makes no warranty of any kind, express or implied, concerning the Product, the information or recommendations provided in this Product Data Sheet or use of the Product, either singly or in combination with other substances. Buyer assumes all risks incident to purchase and use. In no event shall Omega Specialty Products & Services be liable to client, or to any person claiming through client, whether in contract, tort, strict product liability or otherwise, for special, indirect, incidental, consequential or liquidated damages including, but not limited to, any claims for lost profits, demurrage or penalties. All warranties, including any implied warranties of merchant ability or fitness for a particular purpose are expressly disclaimed.